

Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	YS 400	YS 420	YS 450		YS 400	YS 420	YS 450
Thickness	2mm	2mm	2mm	Thickness	2mm	2mm	2mm
Wavelength	%T	%T	%T	Wavelength	%T	%T	%T
200	0.01	0.00	0.00	620	90.82	90.79	90.78
210	0.04	0.00	0.00	630	90.79	90.79	90.81
220	0.04	0.01	0.01	640	90.78	90.81	90.81
230	0.04	0.04	0.00	650	90.81	90.80	90.82
240	0.04	0.04	0.00	660	90.81	90.81	90.80
250	0.04	0.04	0.01	670	90.82	90.83	90.77
260	0.04	0.04	0.04	680	90.80	90.82	90.79
270	0.04	0.04	0.04	690	90.77	90.82	90.79
280	0.03	0.04	0.04	700	90.79	90.83	90.81
290	0.04	0.04	0.04	710	90.79	90.79	90.81
300	0.04	0.03	0.04	720	90.81	90.81	90.83
310	0.05	0.04	0.04	730	90.80	90.80	90.82
320	0.05	0.04	0.04	740	90.81	90.83	90.82
330	0.05	0.05	0.03	750	90.83	90.82	90.83
340	0.05	0.05	0.04	760	90.82	90.82	90.79
350	0.05	0.05	0.04	770	90.82	90.83	90.81
360	0.05	0.05	0.05	780	90.83	90.79	90.80
370	0.05	0.05	0.05	790	90.82	90.81	90.83
380	0.44	0.05	0.05	800	90.81	90.81	90.81
390	7.64	0.05	0.05	810	90.81	90.81	90.82
400	46.01	0.44	0.05	820	90.80	90.82	90.82
410	74.93	7.64	0.05	830	90.79	90.82	90.83
420	85.04	46.01	0.05	840	90.81	90.83	90.79
430	88.75	74.93	0.44	850	90.83	90.79	90.81
440	89.43	85.04	7.64	860	90.81	90.81	90.82
450	90.24	88.75	46.01	870	90.82	90.81	90.82
460	90.75	89.43	74.93	880	90.79	90.81	90.83
470	90.80	90.24	85.04	890	90.80	90.80	90.79
480	90.82	90.75	88.75	900	90.77	90.79	90.81
490	90.70	90.80	89.43	910	90.79	90.81	90.81
500	90.75	90.82	90.24	920	90.81	90.82	90.81
510	90.79	90.70	90.75	930	90.80	90.82	90.80
520	90.80	90.75	90.80	940	90.81	90.83	90.83
530	90.82	90.79	90.82	950	90.81	90.79	90.79
540	90.80	90.80	90.70	960	90.80	90.81	90.81
550	90.83	90.82	90.75	970	90.82	90.81	90.81
560	90.82	90.80	90.79	980	90.80	90.79	90.79
570	90.80	90.83	90.80	990	90.79	90.81	90.81
580	90.80	90.82	90.82	1000	90.81	90.81	90.81
590	90.82	90.80	90.80	1050	90.80	90.81	90.81
600	90.82	90.80	90.83	1100	90.82	90.80	90.80
610	90.79	90.82	90.82	1200	90.80	90.80	90.79